

Product Information

High Performance Lubricants

Molykote[®] Cu-7439 Plus

High Temperature Copper Paste

FEATURES

- Excellent adhesion to metal surfaces
- Wide temperature range (-30 to 650° C)
- Good load-carrying capability

BENEFITS

- Reduces friction and wear
- Excellent protection against fretting corrosion and corrosion due to high temperature
- Helps prevent brake squeal in disc brakes
- Allows trouble-free disassembly of machine components even after long service intervals

High Temperature Copper Paste

APPLICATIONS

- Disc brakes, brake cams, brake guides, flange seals, adjuster screws, and threaded connections
- Vehicle assembly and maintenance (e.g., truck drum brakes)
- In steel works, glass manufacturing, refineries, and petrochemical facilities
- On agricultural and marine vehicles

TYPICAL PROPERTIES

Specification Writers: These values are not intended for use in preparing specifications. Please contact your local Dow Corning sales office or your Global Dow Corning Connection before writing specifications on this product.

Property	Value
Color:	copper
Temperature range:	-30 to +650°C (as paste up to 300°C)
Density (g/cm ³)	0.99
Penetration, unworked (mm/10):	310 - 360
Dropping point:	none
Extreme pressure capability [AWM O.K. -load (lbs.)]	4,400
Four Ball Test, wear scar, 1 hour @ 400N, (mm)	0.6
Press Fit Test, coefficient of friction	0.12
Corrosion tests at 50 um thickness (DIN 50021 salt spray test)	> 500 hours
after heating at 250°C for 1 hour	> 100 hours
SKF Corrosion Test (7 day water test)	0 - 1

DESCRIPTION

Molykote[®] Cu-7439 is a long term lubricant for machine components which are exposed to high loads, high temperatures and corrosive environments. The paste exhibits excellent adhesion to metal surfaces, providing not only good resistance to removal by steam and/or hot water, but increased protection from corrosion.

HOW TO USE

Apply by brush to clean, dry metal surfaces

HANDLING PRECAUTIONS

Product safety information required for safe use is not included. Before handling, read product and safety data sheets and container labels for safe use, physical and health hazard information. The material safety data sheet is available on the Dow Corning website at www.dowcorning.com. You can also obtain a copy from your local Dow Corning sales representative or Distributor or by calling your local Dow Corning Global Connection.

USABLE LIFE AND STORAGE

Molykote[®] Cu-7439 has a shelf life of 60 months when kept in its original, sealed container.

PACKAGING

Molykote[®] Cu-7439 is supplied in 16 kg (35.2 lb) open-top pails.

LIMITATIONS

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

HEALTH AND ENVIRONMENTAL INFORMATION

To support Customers in their product safety needs, Dow Corning has an extensive Product Stewardship organization and a team of Product Safety and Regulatory Compliance (PS&RC) specialists available in each area.

For further information, please see our website, www.dowcorning.com or consult your local Dow Corning representative.

LIMITED WARRANTY INFORMATION - PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that Dow Corning's products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow Corning's sole warranty is that the product will meet the Dow Corning sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

DOW CORNING SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY.

DOW CORNING DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.

We help you invent the future.[™]

www.dowcorning.com